X : Prohibited

IMO	UN No.	Proper Shipping Name	ONE
	WASTE	All waste cargoes govern by Basel Convention is prohibited unless written consent is received from competence authority of the state exporting, importing and transiting states. GDG shall confirm vessel owner's acceptance. (If required by CP.) Following documents shall be prepared by sales (Shipper) and confirmed by GDG a) Movement document issued by the state of export b) Import permission by import country c) Transit permission in transit countries d) Stowage: On deck Away from Heat for Battery Waste e) Waste lithium batteries are prohibited.	R
	Requirement of Vanning survey	 Vanning Survey is required as below condition. 1) Should be done by competent marine surveyor as the third party. e.g. NKKK(Nippon Kaiji Kentei Kyokai) or SK(Shin Nihon Kentei Kyokai) in Japan, NCB(National Cargo Bureau) in U.S.A. 2) All packages have been externally inspected for damage, and only sound packages have been packed. 3) The container should be clean, dry and apparently fit to receive the goods. 4) The container and packages therein are properly marked, labelled and placard. 5) All packages shall be properly secured in the container to avoid any movement during sea transport which would change the orientation of the packages or cause them to be damaged. 6) Survey report should be submitted to GDG. 7) Additional requirement if any. 	R
	Flexi-tank	Prohibited DG in Flexi-Tank	X
	DG in Heating tank container	 To be stowed on deck / 1st tier Copy of periodic Tank inspection and CSC approval plate SDS (Safety Data Sheets) If require electric supply from vessel, following documents shall be provided to GDG that require GCAA approval, Vessel master L/G stating that the ship's operator has no responsibility on this shipment in case of temperature control unit malfunction. 	R
	Temperature controlled DG (Live Dual Reefer)	 Explosive-proof type Dual Reefer container (SOC) shall be used. Below items shall be provided to GDG that require GCAA approval and vessel master; a) SDS b) SAPT or SADT, control, and emergency temperature. c) Reefer operating manual. d) Reefer spare parts and emergency contact. e) Crew training conducted for dual reefer operation, retraining is required only after 3 months. f) Explanation of the weight packages, type, and condition of stuffing. g) Jettison Letter from the shipper. h) Transhipment is prohibited. 3. Void space may be necessary in order to open the container door during an emergency. 4. Max. number of this DG is 20ft x 2 units per voyage. 	R
	SP386 (Temperature Controlled)	Where polymerization may occur at lower temperatures: i) SAPT is 50°C or less in the packaging or IBC; ii) SAPT is 45°C or less in the portable tank. See Temperature Controlled DG (above) when loading in "live" reefers.	R
	DG acceptable in live reefer (Normal Reefer unit)	 Class 3 (Flash Point < 23 deg C) include Sub risk as Class 3 (Flash Point < 23 deg C); a) SDS - A control temperature shall be set at least 10 deg C below the Flash Point b) Acceptance subject to full compliance with IMDG code 7.3.7.6.2 Class 3 (FP>=23) include Sub risk as Class 3 (FP>=23); Reefer setting temperature should be lower than Flash Point of the cargo (Confirm by SDS) Flammable gas Class 2.1 (including subhazard) for quality purposes must comply with IMDG 7.3.7.6.3, an explosion-proof reefer is required. Other DG in reefer for the sole purpose of quality control with no sub-explosive risk is acceptable. Ventilation mode is "CLOSE" for live reefers. For ONE reefer unit (include Reefer as Dry), after devanning DG cargo from reefer container, the container interior & evaporator air stream compartment have to be thoroughly checked, cleaned-up and removed odour. MnR Team at discharge port should be notified. (This is compulsory because it will affect the next shipment which can well be foodstuff cargo.) 	R

X : Prohibited

IMO	UN No.	Proper Shipping Name	ONE
		Below applicable if Freight Container used as BK1 or BK2	
	DG in BULK Cargoes	 Acceptable loading in SOC (Shipper Owned Container) container only Require to compliance all the requirement as per IMDG Code under chapter 6.9.3 To provide stuffing photos to show the proper protection on the container interior from leaking 	R
	Military Goods	All ammunition, explosive or propellent for arms, weapon and military goods used for military purpose. Prohibition -Mass Destructino & Arms & Ammunition -Goods that cause political conflicts -Sanction Goods	X
1.1	All	-Goods which are prohibited by owner Substances and articles which have a mass explosion hazard	X
1.2	All	Substances and articles which have a projection hazard but not a mass explosion hazard	x
1.3 1.4	All	Cargo to/from/tranship/pass Black Sea ports and Istanbul include Bosporus strait, Dardanelles/Canakkale strait (include other commodity with "explosive" sub labels / sub-risk 1)	x
1.5 1.6	All	 Vanning survey is required. (include other commodity with "explosive" sub labels / sub-risk 1) Class 1 might be restricted/prohibited depending on space availability by segregation with other dangerous cargo, vessel owner's requirements and trade, port/terminal restriction. 	R
	ALL	Cargo to/from/tranship/pass Black Sea ports and Istanbul include Bosporus strait	x
	1966 1972	HYDROGEN, REFRIGERATED LIQUID METHANE, REFRIGERATED LIQUID or NATURAL GAS, REFRIGERATED LIQUID with high methane content	R R
2.1		 For Laden shipment in ISO Tank prior approval by GCAA is required via GDG, and Shipper should provide the following documents; a) SDS b) Operation manual of ISO Tank c) Tank certificate d) Setting pressure of safety relief valve 2. For Empty shipment, not require GCAA approval. 	
2.2	All	Cargo to/from/tranship/pass Black Sea ports and Istanbul include Bosporus strait	x
	1963	 HELIUM, REFRIGERATED LIQUID 1. The below restrictions apply to laden tanks only. 2. Transhipment prohibited unless approve by GCAA. 3. If require on-board monitoring, GCAA approval must be obtained. 4. On deck stowage (1st or 2nd tier for monitoring purpose) 5. The following acceptance requirement is applicable for ISO Tank Refrigerated Liquid Helium Shipment with below MAX PSI 91 (≤91): a) At the time of loading from the Port of Origin (POR/POL), the PSI reading for the shipment must be below 10 PSI (≤10). b) For approved transshipment of Helium Shipment (UN1963), PSI reading must be below 35 PSI (≤35) at the time of loading (T/S Port) unless approve by GCAA. c) Shipper should make arrangements with the terminal (POR/POL or T/S) to release the pressure when container is in the yard before loading. 	R
	2455	METHYL NITRITE	X
	ALL	Cargo to/from/tranship/pass Black Sea ports and Istanbul include Bosporus strait	X
2.3	ALL	 Following requirements are applied, if it is origin from P.R.China include Hong Kong 1. In Dry GP box (Not applicable if it is empty receptacles.) a) Vanning survey 2. In ISO tank or MEGC. a) Valid tank periodic inspection certificate. b) Pre-loading inspection report by surveyor certify safe physical condition for sea transport. 	R
	2186	HYDROGEN CHLORIDE, REFRIGERATED LIQUID	X

X : Prohibited

IMO	UN No.	Proper Shipping Name	ONE
	2956	5-tert-BUTYL-2,4,6-TRINITRO-m-XYLENE (MUSK XYLENE)	R
		If carrying a subsidiary risk label of class 1, see Class 1.	
	3221	SELF-REACTIVE LIQUID TYPE B	R
	3222	SELF-REACTIVE SOLID TYPE B	R
		If carrying a subsidiary risk label of class 1, see Class 1.	
	3231	SELF-REACTIVE LIQUID TYPE B, TEMPERATURE CONTROLLED	R
	3232 3233	SELF-REACTIVE SOLID TYPE B, TEMPERATURE CONTROLLED SELF-REACTIVE LIQUID TYPE C, TEMPERATURE CONTROLLED	R R
	3233	SELF-REACTIVE SOLID TYPE C, TEMPERATURE CONTROLLED	R
	3235	SELF-REACTIVE LIQUID TYPE D, TEMPERATURE CONTROLLED	R
	3236	SELF-REACTIVE SOLID TYPE D, TEMPERATURE CONTROLLED	R
	3237	SELF-REACTIVE LIQUID TYPE E, TEMPERATURE CONTROLLED	R
	3238 3239	SELF-REACTIVE SOLID TYPE E, TEMPERATURE CONTROLLED SELF-REACTIVE LIQUID TYPE F, TEMPERATURE CONTROLLED	R R
	3239	SELF-REACTIVE SOLID THE F, TEMPERATURE CONTROLLED	R
	5210		к
4.1		Only for UN3231, UN3232, if apply as Sub risk Class 1, see Class 1.	
4.1		Acceptable ONE's booking on ONE-operated vessels & subject to prior approval by GCAA. See Temperature Controlled DG (above).	
F	3531	POLYMERIZING SUBSTANCE, SOLID, STABILIZED, N.O.S.	R
	3532	POLYMERIZING SUBSTANCE, LIQUID, STABILIZED, N.O.S.	
			R
	3533	POLYMERIZING SUBSTANCE, SOLID, TEMPERATURE CONTROLLED, N.O.S.	R
	3534	POLYMERIZING SUBSTANCE, LIQUID, TEMPERATURE CONTROLLED, N.O.S.	R
		Divinylbenzene (DVB) (Diethenylbenzene / Vinylstyrene.) should be classified under Class 4.1/UN 3532 or Class	
		4.1/UN 3534.	
		Exception if accompanied by: - product-specific classification Test Report by Competent Authority, or	
		- product-specific classification Test Report by a laboratory accredited by a Competent Authority	
		(The test report shall mention IMO classes other than class 4.1)	
		Divinylbenzene shall be stowed on deck only regardless of IMO class.	
		If loading in "live" reefers:	
		i) Acceptable ONE's booking on ONE-operated vessels & subject to prior approval by GCAA.	
		ii) See Temperature Controlled DG (above).	
	1361	CARBON animal or vegetable origin.	R
		The below requirements are applied to Charcoal (UN 1361).	
		1. 20' CTNR only 2. Obtain SDS	
		3. Obtain the Shipper's certificate stating:	
		a) proper curing and weathering (cooling) period of at least a total of 28 days between taking out of oven chamber	
		and stuffing into the container.	
		4. When charcoal is stuffed into a CTNR, more than 30cm of vacant space between the cargo and the CTNR ceiling	
		should be secured.	
		 5. Not packed together with charcoal lighter or other ignition agent. 6. Vanning survey is required additional requirement if any: Photo showing above Item 4 & Item 5) 	
		7. On Deck 1st TIER only (Shaded from direct sunlight/sources of heat).	
		8. Charcoal from Indonesia is prohibited.	
	1362	CARBON, ACTIVATED	R
		UN 1361 & UN1362 - Stowage On Deck only and away from sources of heat (ODAB)	1
		<for charcoal="" non-dg=""> Not acceptable.</for>	
		<for carbon="" non-dg=""> - Accepted subject to compliance with SP925 of the IMDG code.</for>	
		Stowage On Deck only and away from sources of heat (ODAB)	
4.2	3088	SELF-HEATING SOLID, ORGANIC, N.O.S.	R
		Below requirements applied if the Technical Name are "Charcoal"	1
		1. 20' CTNR only	
		2. Obtain SDS	
		3. Obtain Shipper's certificate stating:	
		a) proper curing and weathering (cooling) period of at least a total of 28 days between taking out of oven chamber and stuffing into the container.	
		4. When charcoal is stuffed into a CTNR, more than 30cm of vacant space between the cargo and the CTNR ceiling	
		should be secured.	
		5. Not packed together with charcoal lighter or other ignition agent.	
		6. Vanning survey is required additional requirement if any": Photo showing above Item 4 & Item 5)	
L		7. On Deck 1st TIER only (Shaded from direct sunlight/sources of heat)	
ſ	1381	PHOSPHORUS, WHITE or YELLOW, DRY or UNDER WATER or IN SOLUTION	R
		1. On deck only	1
		2. In case of Dry Container :	
		a. A new drum shall be used when packed in a steel package.	
		b. The cargo shall be stuffed one tier only.	
		c. Vanning survey is required additional requirement if any: Photo showing above Item a & Item b)	

X : Prohibited

1415 ITHINM 3 1418 MAONESIUM POWDER or MAGNESIUM ALLOYS POWDER 3 1. Fire fighting material Libitum chloride powder, dry sodium chloride or graphite powder must be provided on bars are provided on bars per IMDG requirement. 20 kg per 20 (1 TEU) under the care of master. 4.1. Cargo to from/tranship/pass Black Sea ports and Istanbul include Bosporas strait 1512 ZINC AMMONIUM NITRITE 1479 OXDIZINS COLD N.O.S. (Applicable in case of Calcium Hypochlorite) CALCIUM HYPOCHLORITE, BRY with more than 95% available chlorine or CALCIUM HYPOCHLORITE, MYR with more than 95% available chlorine or CALCIUM HYPOCHLORITE, HYDRATED with not be some than 95% available chlorine or CALCIUM HYPOCHLORITE, HYDRATED MINTURE, DRY with more than 55% but not more than 16% water or CALCIUM HYPOCHLORITE, HYDRATED MINTURE, With more than 35% available chlorine or CALCIUM HYPOCHLORITE, MIXTURE, DRY, CORROSIVE with more than 35% but not more than 16% water or CALCIUM HYPOCHLORITE, MIXTURE, DRY, CORROSIVE with more than 55% but not more than 16% water or CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with more than 55% but not more than 16% water or CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with more than 55% but not more than 16% water or CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with more than 55% but not more than 16% water or CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORITE, HYDRATE DIMINTURE, CORROSIVE with not less than 5.5% but
as per IMDG requirement. 20 kgs per 20 (1 TEU) under the care of master. 2. Acceptable for 1st leg vessel only (if require 2nd leg vessel, shall consult GDG that require GCAA approval.) ALL Cargo toffrom/tranship/pass Black Sea ports and Stanbal include Bosporus strait 112 ZINC AMMONIUM INTERTE 1479 CMUDZING SCILD, NO.5. (Applicable in case of Calcium Hypochlorit) CALCUM HYPOCHLORITE MIXTURE, DRY with more than 39% available chlorine 2008 CALCUM HYPOCHLORITE MIXTURE, DRY with more than 39% available chlorine 2018 CALCUM HYPOCHLORITE MIXTURE, DRY with more than 39% available chlorine 2016 CALCUM HYPOCHLORITE MIXTURE, DRY, CORROSIVE with more than 39% available chlorine 2017 CALCUM HYPOCHLORITE HYDRATURE, DRY, CORROSIVE with more than 39% available chlorine 2018 CALCUM HYPOCHLORITE HYDRATURE, DRY, CORROSIVE with more than 39% available chlorine 2014 CALCUM HYPOCHLORITE HYDRATURE, DRY, CORROSIVE with more than 39% available chlorine 2016 CALCUM HYPOCHLORITE, HYDRATED CORROSIVE with more than 55% but not more than 10% water 3487 CALCUM HYPOCHLORITE, HYDRATED CORROSIVE with not less than 5.5% but not more than 10% water 3487 CALCUM HYPOCHLORITE, HYDRATED CORROSIVE with not less than 5.5% but not more than 10% water 3487 CALCUM HYPOCHLORITE, HYDRATED CORROSIVE with n
1512 ZINC AMMONIUM NITRITE 1479 OXIDZING SULID, NO.S. (Applicable in case of Calcium Hypochlorite) 1748 CALCUM HYPOCHLORITE, DRY with more than 39% available chlorine 2208 CALCUM HYPOCHLORITE, DRY with more than 39% available chlorine 2208 CALCUM HYPOCHLORITE, HYDRATED with more than 39% available chlorine 2800 CALCUM HYPOCHLORITE, HYDRATED with nore than 39% available chlorine 3485 CALCUM HYPOCHLORITE DRY, CORROSIVE with more than 39% available chlorine 3486 CALCUM HYPOCHLORITE MYTURE, DRY, CORROSIVE with more than 16% water 3486 CALCUM HYPOCHLORITE MYTURE, DRY, CORROSIVE with more than 16% water 3487 CALCUM HYPOCHLORITE, HYDRATED CORROSIVE with more than 16% water 3487 CALCUM HYPOCHLORITE, HYDRATED CORROSIVE with more than 16% water 10 Acceptance of Calcium Hypochlorie subject to the evaluation of following condition by GDG that require GC approval. 1 Acceptance of Calcium Hypochlorie subject to the evaluation of following condition by GDG that require GC approval. 1 Acceptance of Calcium Hypochlorie subject to the evaluation of following condition by GDG that require GC approval. 1 Recentare of Calcium Hypochlorie subject to the evaluation of following condition by GDG that require GC approval. 2
1479 OXIDIZING SOLID. NO.S. (Applicable in case of Calcium Hypochlorite) 1748 CALCIUM HYPOCHLORITE BNY with more than 39% available chlorine or CALCIUM HYPOCHLORITE MIXTURE. DRY with more than 39% available chlorine 2008 CALCIUM HYPOCHLORITE HYDRATED with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORITE, HYDRATED with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORITE, HYDRATED WIXTURE with not less than 5.5% but not more than 16% water 3485 CALCIUM HYPOCHLORITE, DRY, CORROSIVE with more than 39% available chlorine or CALCIUM HYPOCHLORITE MIXTURE, DRY, CORROSIVE with more than 16% water 3486 CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with more than 39% available chlorine 3487 CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with more than 39% available chlorine 3487 CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with mote less than 5.5% but not more than 16% water 3487 CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with mot less than 5.5% but not more than 16% water 3488 CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with mote less than 5.5% but not more than 16% water 1 Acceptance of Calcium Hypochlorite subject to the evaluation of following condition by GDG that require GC approval; 1. Result of heat accumulation storage test by 3rd party surveyor 2. Submission of SDS 3. 20ft container only and leaded from direct sumight) 6. Application will be reviewed on a case by case basis d
1748 CALCIUM HYPOCHLORTE, DRY with more than 39% available chlorine or CALCIUM HYPOCHLORTE MIXTURE, DRY with more than 39% available chlorine 2208 CALCIUM HYPOCHLORTE MIXTURE, DRY with more than 10% but not more than 39% available chlorine 2880 CALCIUM HYPOCHLORTE, HYDRATED with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORTE, HYDRATED MIXTURE with not less than 5.5% but not more than 16% water 3485 CALCIUM HYPOCHLORTE, DRY, CORROSIVE with more than 39% available chlorine or CALCIUM HYPOCHLORTE, MIXTURE, DRY, CORROSIVE with more than 39% available chlorine 3486 CALCIUM HYPOCHLORTE, HYDRATED, CORROSIVE with more than 39% available chlorine 3487 CALCIUM HYPOCHLORTE, HYDRATED, CORROSIVE with more than 10% but not more than 16% water or CALCIUM HYPOCHLORTE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORTE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORTE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORTE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORTE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORTE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORTE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORTE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORTE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORTE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water or CALCIUM KINGATA,
1/48 CALCIUM HYPOCHLORITE MIXTURE, DRY with more than 5% available chlorine 2208 CALCIUM HYPOCHLORITE MIXTURE, DRY with more than 10% but not more than 16% water or 2880 CALCIUM HYPOCHLORITE, HYDRATED with not less than 5.5% but not more than 16% water or 3485 CALCIUM HYPOCHLORITE, HYDRATED MIXTURE, with not less than 5.5% but not more than 16% water 3486 CALCIUM HYPOCHLORITE MIXTURE, DRY, CORROSIVE with more than 39% available chlorine 3486 CALCIUM HYPOCHLORITE MIXTURE, DRY, CORROSIVE with more than 10% but not more than 39% available chlorine 3487 CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with more than 16% water 3487 CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water 1 Acceptance of Calcium Hypochloric subject to the evaluation of following condition by GDG that require GC approval; 1 Result of heat accumulation storage test by 3rd party surveyor 2 Submission of SDS 3 30 ronianier only and 14 Tons net weight per package 5 On deck protect stowage (shaded from direct sunlight) 6 Application will be reviewed on a case by case basis depending on trade lanes and ship's owners' requirements 7 For loading on ONE chardet essels, Will require 5 working days to obtain owners approval.
2208 CALCIUM HYPOCHLORITE, HYDRATED with not less than 5.5% but not more than 16% water or CALCIUM HYPOCHLORITE, HYDRATED MIXTURE with not less than 5.5% but not more than 16% water 3485 CALCIUM HYPOCHLORITE, DRY, CORROSIVE with more than 39% available chlorine or CALCIUM HYPOCHLORITE MIXTURE, DRY, CORROSIVE with more than 39% available chlorine 3486 CALCIUM HYPOCHLORITE MIXTURE, DRY, CORROSIVE with more than 10% but not more than 39% available chlorine 3487 CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with more than 15% but not more than 16% water 3487 CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water 1 Acceptance of Calcium Hypochlorite subject to the evaluation of following condition by GDG that require GC approval. 1. Result of heat accumulation storage test by 3rd party surveyor 2. submission of SDS 3. 20fit container only and 14 Tons net weight per container 4. Each Packages should not exceed 45 kgs net weight per package 5. On deck protect stowage (shaded from direct sunlight) 6. Application will be reviewed on a case by conking duys to obtain owners approval. 8. Transhipment prohibide, except Pasan/Hong Kong/Singapore (apply to ONE B.L only) 9. Japan Origin only 1942 AMMONIUM NITRATE BASED FERTILIZER 2466 AMMONIUM NITRATE BASED FERTILIZER 33778 SODUUM CARBOANTE PEROXTHYDRATE 976 Prohibide from
ALCIUM HYPOCHLORITE, HYDRATED MIXTURE with not less than 5.5% but not more than 16% water 3485 CALCIUM HYPOCHLORITE, DRY, CORROSIVE with more than 39% available chlorine or CALCIUM HYPOCHLORITE MIXTURE, DRY, CORROSIVE with more than 39% available chlorine 3486 CALCIUM HYPOCHLORITE MIXTURE, DRY, CORROSIVE with more than 16% but not more than 39% available chlorine 3487 CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with more than 16% water calculum HYPOCHLORITE, HYDRATED MIXTURE, CORROSIVE with not less than 5.5% but not more than 16% water 1 Acceptance of Calcium Hypochlorite subject to the evaluation of following condition by GDG that require GC approval; 1. Result of heat accumulation storage test by 3rd party surveyor 2. submission of SDS 2. Softmission of SDS 3.0ft container only and 14 Tons net weight per container 4. Each Packages should not exceed 4 Sps net weight per package 5. On deck protect stowage (shaded from direct sullight) 6. Application will be reviewed on a case by case bisis depending on trade lanes and ship's owners' requirements 7. For loading on ONE charted vessels, Will require 5 working days to obtain owners approval. 8. Transhipment prohibited. except Pusan/Hong Kong/Singapore (apply to ONE B/L only) 9. Japan ONE charted vessels, Will require 5 working days to obtain owners approval. 9.0246 AMMONIUM NITRATE BASED FERTILIZER AMMONIUM NITRATE BASED FERTILIZER 1942 AMMONIUM NITRATE B
ALCIUM HYPOCHLORITE MIXTURE, DRY, CORROSIVE with more than 39% available chlorine 3486 CALCIUM HYPOCHLORITE MIXTURE, DRY, CORROSIVE with more than 10% but not more than 39% available chlorine 3487 CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water of CALCIUM HYPOCHLORITE, HYDRATED MIXTURE, CORROSIVE with not less than 5.5% but not more than 16% water 1 Acceptance of Calcium Hypochlorite subject to the evaluation of following condition by GDG that require GC approval; 1. Result of heat accumulation storage test by 3rd party surveyor 2. Submission of SDS 3. 20ft container only and 14 Tons net weight per container 4. Each Packages should not exceed 45 kgs net weight per package 5. On deck protect stowage (shaded from direct sungipt) 6. Application will be reviewed on a case by case basis depending on trade lanes and ship's owners' requirements 7. For loading on ONE charted vessels, Will require 5 working days to obtain owners approval. 8. Transhipment prohibited, except Plusan/Hong Kong/Singapore (apply to ONE B/L only) 9. Japan Origin only 9. Japan Origin only 9. Japan Origin only 1942 AMMONIUM NITRATE BASED FERTILIZER 2067 AMMONIUM NITRATE BASED FERTILIZER 21942 AMMONIUM NITRATE BASED FERTILIZER 2104 (stabilized as necessary) Prohibited from ALL CHINA Origin includine HKH
3486 CALCIUM HYPOCHLORITE MIXTURE, DRY, CORROSIVE with more than 10% but not more than 39% availal chlorine 3487 CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water c 1 CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water Acceptance of Calcium Hypochlorite subject to the evaluation of following condition by GDG that require GC approval; I. Result of heat accumulation storage test by 3rd party surveyor 2. Submission of SDS 3. 20ft container only and 14 Tons net weight per container 4. Each Packages should not exceed 45 kgs net weight per package 5. On deck protect stowage (shaded from direct sunlight) 6. Application will be reviewed on a case by case basis depending on trade lanes and ship's owners' requirements 7. For loading on ONE charted vessels, Will require 5 working days to obtain owners approval. 8. Transhipment prohibited, except Pusan/Hong Kong/Singapore (apply to ONE B/L only) 9. Japan Origin only 9. Japan Origin only 9. Japan Origin only 1942 AMMONIUM NITRATE ASSODIUM CARBONATE PEROXYHYDRATE 2057 AMMONIUM NITRATE PEROXYHYDRATE Polabited from ALL CHINA Origin includine HKHKG 9. Torolading on ONE chared vessels, Will require 5 working days to obtain owners approval. 9. Torolading on Origin ex-Bangladesh. 1010 ORGANIC PEROXIDE TYPE BLUQUID
3487 CALCIUM HYPOCHLORITE, HYDRATED, CORROSIVE with not less than 5.5% but not more than 16% water of CALCIUM HYPOCHLORITE, HYDRATED MIXTURE, CORROSIVE with not less than 5.5% but not more than 16% water of calcium Hypochlorite subject to the evaluation of following condition by GDG that require GC approval; I. Acceptance of Calcium Hypochlorite subject to the evaluation of following condition by GDG that require GC approval; I. Result of heat accumulation storage test by 3rd party surveyor 2. Submission of SDS 3. 20ft container only and 14 Tons net weight per container 4. Each Packages should not exceed 45 kgs net weight per package 5. On deck protect stowage (shaded from direct sunlight) 6. Application will be reviewed on a case by case basis depending on trade lanes and ship's owners' requirements 7. For loading on ONE charted vessels, Will require 5 working days to obtain owners approval. 8. Transhipment prohibited, except Pusan/Hong Kong/Singapore (apply to ONE B/L only) 9. Japan Origin only 1942 AMMONIUM NITRATE 2067 AMMONIUM NITRATE LASED FERTILIZER 3378 SODIUM CARBONATE PEROXTHYDRATE 7 For loading on ONE charted vessels, Will require 5 working days to obtain owners approval. 3101 ORGA
Acceptance of Calcului Hypochiotic subject to the evaluation of following condution by GDS that require oc approval; 1. Result of heat accumulation storage test by 3rd party surveyor 2. Submission of SDS 3. 20ft container only and 14 Tons net weight per container 4. Each Packages should not exceed 45 kgs net weight per package 5. On deck protect stowage (shaded from direct sunlight) 6. Application will be reviewed on a case by case basis depending on trade lanes and ship's owners' requirements 7. For loading on ONE charted vessels, Will require 5 working days to obtain owners approval. 8. Transhipment prohibited, except Pusan/Hong Kong/Singapore (apply to ONE B/L only) 9. Japan Origin only 9. Japan Origin only 1942 AMMONIUM NITRATE 2067 AMMONIUM NITRATE 2067 AMMONIUM NITRATE 2067 AMMONIUM ACABONATE PEROXYHYDRATE Prohibited from ALL CHINA Origin including HKHKG HYDROGEN PEROXIDE, AQUEOUS SOLUTION with not less than 20% but not more than 60% hydrogen peros 2014 (stabilized as necessary) Prohibited from Origin ex-Bangladesh. ALL Cargo to/from/tranship/pass Black Sea ports and Istanbul include Bosporus strait
1942 AMMONIUM NITRATE 2067 AMMONIUM NITRATE BASED FERTILIZER 2426 AMMONIUM NITRATE, LIQUID (hot concentrated solution) For loading on ONE charted vessels, Will require 5 working days to obtain owners approval. 3378 SODIUM CARBONATE PEROXYHYDRATE Prohibited from ALL CHINA Origin including HKHKG HYDROGEN PEROXIDE, AQUEOUS SOLUTION with not less than 20% but not more than 60% hydrogen perox (stabilized as necessary) Prohibited from Origin ex-Bangladesh. ALL Cargo to/from/tranship/pass Black Sea ports and Istanbul include Bosporus strait 3101 ORGANIC PEROXIDE TYPE B, LIQUID 3102 ORGANIC PEROXIDE TYPE B, SOLID 3103 ORGANIC PEROXIDE TYPE C, LIQUID 3104 ORGANIC PEROXIDE TYPE C, SOLID 3105 ORGANIC PEROXIDE TYPE D, LIQUID 3106 ORGANIC PEROXIDE TYPE D, LIQUID 3107 ORGANIC PEROXIDE TYPE E, SOLID 3108 ORGANIC PEROXIDE TYPE E, SOLID 3109 ORGANIC PEROXIDE TYPE F, LIQUID 3109 ORGANIC PEROXIDE TYPE F, SOLID
2067 AMMONIUM NITRATE BASED FERTILIZER 2426 AMMONIUM NITRATE, LIQUID (hot concentrated solution) For loading on ONE charted vessels, Will require 5 working days to obtain owners approval. 3378 SODIUM CARBONATE PERCOXIPHYDRATE Prohibited from ALL CHINA Origin including HKHKG HYDROGEN PEROXIDE, AQUEOUS SOLUTION with not less than 20% but not more than 60% hydrogen perov 2014 (stabilized as necessary) Prohibited from Origin ex-Bangladesh. ALL Cargo to/from/tranship/pass Black Sea ports and Istanbul include Bosporus strait 3101 ORGANIC PEROXIDE TYPE B, SOLID 3102 ORGANIC PEROXIDE TYPE B, SOLID 3103 ORGANIC PEROXIDE TYPE B, SOLID 3104 ORGANIC PEROXIDE TYPE C, LIQUID 3105 ORGANIC PEROXIDE TYPE D, LIQUID 3104 ORGANIC PEROXIDE TYPE C, SOLID 3105 ORGANIC PEROXIDE TYPE D, SOLID 3106 ORGANIC PEROXIDE TYPE D, SOLID 3107 ORGANIC PEROXIDE TYPE E, SOLID 3108 ORGANIC PEROXIDE TYPE E, SOLID 3109 ORGANIC PEROXIDE TYPE E, SOLID 3109 ORGANIC PEROXIDE TYPE F, LIQUID 3109 ORGANIC PEROXIDE TYPE F, SOLID 3
2426 AMMONIUM NITRATE, LIQUID (hot concentrated solution) For loading on ONE charted vessels, Will require 5 working days to obtain owners approval. 3378 SODIUM CARBONATE PEROXPHYDRATE Prohibited from ALL CHINA Origin including HKHKG HYDROGEN PEROXIDE, AQUEOUS SOLUTION with not less than 20% but not more than 60% hydrogen perov (stabilized as necessary) Prohibited from Origin ex-Bangladesh. ALL Cargo to/from/tranship/pass Black Sea ports and Istanbul include Bosporus strait 3101 ORGANIC PEROXIDE TYPE B, LIQUID 3102 ORGANIC PEROXIDE TYPE B, SOLID 3103 ORGANIC PEROXIDE TYPE C, LIQUID 3104 ORGANIC PEROXIDE TYPE C, SOLID 3105 ORGANIC PEROXIDE TYPE D, LIQUID 3106 ORGANIC PEROXIDE TYPE D, SOLID 3107 ORGANIC PEROXIDE TYPE D, SOLID 3108 ORGANIC PEROXIDE TYPE E, SOLID 3109 ORGANIC PEROXIDE TYPE E, SOLID 3109 ORGANIC PEROXIDE TYPE E, SOLID
3378 SODIUM CARBONATE PEROXYHYDRATE Prohibited from ALL CHINA Origin including HKHKG 4 HYDROGEN PEROXIDE, AQUEOUS SOLUTION with not less than 20% but not more than 60% hydrogen perov (stabilized as necessary) Prohibited from Origin ex-Bangladesh. 4 Cargo to/from/tranship/pass Black Sea ports and Istanbul include Bosporus strait 3101 ORGANIC PEROXIDE TYPE B, LIQUID 3102 ORGANIC PEROXIDE TYPE B, SOLID 3103 ORGANIC PEROXIDE TYPE B, SOLID 3104 ORGANIC PEROXIDE TYPE C, SOLID 3105 ORGANIC PEROXIDE TYPE D, LIQUID 3106 ORGANIC PEROXIDE TYPE D, LIQUID 3107 ORGANIC PEROXIDE TYPE D, LIQUID 3108 ORGANIC PEROXIDE TYPE E, SOLID 3109 ORGANIC PEROXIDE TYPE E, SOLID 3109 ORGANIC PEROXIDE TYPE E, SOLID 3109 ORGANIC PEROXIDE TYPE E, SOLID
HYDROGEN PEROXIDE, AQUEOUS SOLUTION with not less than 20% but not more than 60% hydrogen perov 2014 (stabilized as necessary) Prohibited from Origin ex-Bangladesh. ALL Cargo to/from/tranship/pass Black Sea ports and Istanbul include Bosporus strait 3101 ORGANIC PEROXIDE TYPE B, LIQUID 3102 ORGANIC PEROXIDE TYPE B, SOLID 3103 ORGANIC PEROXIDE TYPE B, SOLID 3104 ORGANIC PEROXIDE TYPE C, LIQUID 3105 ORGANIC PEROXIDE TYPE D, LIQUID 3106 ORGANIC PEROXIDE TYPE D, LIQUID 3107 ORGANIC PEROXIDE TYPE D, SOLID 3108 ORGANIC PEROXIDE TYPE E, SOLID 3109 ORGANIC PEROXIDE TYPE E, SOLID 3108 ORGANIC PEROXIDE TYPE E, SOLID 3109 ORGANIC PEROXIDE TYPE F, LIQUID 3100 ORGANIC PEROXIDE TYPE F, SOLID
2014 (stabilized as necessary) Prohibited from Origin ex-Bangladesh. ALL Cargo to/from/tranship/pass Black Sea ports and Istanbul include Bosporus strait 3101 ORGANIC PEROXIDE TYPE B, LIQUID 3102 ORGANIC PEROXIDE TYPE B, SOLID 3103 ORGANIC PEROXIDE TYPE C, LIQUID 3104 ORGANIC PEROXIDE TYPE C, SOLID 3105 ORGANIC PEROXIDE TYPE D, SOLID 3106 ORGANIC PEROXIDE TYPE D, SOLID 3107 ORGANIC PEROXIDE TYPE D, SOLID 3108 ORGANIC PEROXIDE TYPE E, LIQUID 3109 ORGANIC PEROXIDE TYPE E, SOLID 3109 ORGANIC PEROXIDE TYPE F, SOLID
ALL Cargo to/from/tranship/pass Black Sea ports and Istanbul include Bosporus strait 3101 ORGANIC PEROXIDE TYPE B, LIQUID 3102 ORGANIC PEROXIDE TYPE B, SOLID 3103 ORGANIC PEROXIDE TYPE C, LIQUID 3104 ORGANIC PEROXIDE TYPE C, SOLID 3105 ORGANIC PEROXIDE TYPE D, LIQUID 3106 ORGANIC PEROXIDE TYPE D, SOLID 3107 ORGANIC PEROXIDE TYPE E, SOLID 3108 ORGANIC PEROXIDE TYPE E, SOLID 3109 ORGANIC PEROXIDE TYPE E, SOLID 3109 ORGANIC PEROXIDE TYPE F, LIQUID 3109 ORGANIC PEROXIDE TYPE F, SOLID 3109 ORGANIC PEROXIDE TYPE F, SOLID 3100 ORGANIC PEROXIDE TYPE F, SOLID
3101 ORGANIC PEROXIDE TYPE B, LIQUID 3102 ORGANIC PEROXIDE TYPE B, SOLID 3103 ORGANIC PEROXIDE TYPE C, LIQUID 3104 ORGANIC PEROXIDE TYPE C, SOLID 3105 ORGANIC PEROXIDE TYPE D, LIQUID 3106 ORGANIC PEROXIDE TYPE E, SOLID 3107 ORGANIC PEROXIDE TYPE E, LIQUID 3108 ORGANIC PEROXIDE TYPE E, SOLID 3109 ORGANIC PEROXIDE TYPE F, LIQUID 3100 ORGANIC PEROXIDE TYPE F, SOLID
3102ORGANIC PEROXIDE TYPE B, SOLID3103ORGANIC PEROXIDE TYPE C, LIQUID3104ORGANIC PEROXIDE TYPE C, SOLID3105ORGANIC PEROXIDE TYPE D, LIQUID3106ORGANIC PEROXIDE TYPE E, SOLID3107ORGANIC PEROXIDE TYPE E, LIQUID3108ORGANIC PEROXIDE TYPE E, SOLID3109ORGANIC PEROXIDE TYPE F, LIQUID3110ORGANIC PEROXIDE TYPE F, SOLID
3103ORGANIC PEROXIDE TYPE C, LIQUID3104ORGANIC PEROXIDE TYPE C, SOLID3105ORGANIC PEROXIDE TYPE D, LIQUID3106ORGANIC PEROXIDE TYPE D, SOLID3107ORGANIC PEROXIDE TYPE E, LIQUID3108ORGANIC PEROXIDE TYPE E, SOLID3109ORGANIC PEROXIDE TYPE F, LIQUID3110ORGANIC PEROXIDE TYPE F, SOLID
3104ORGANIC PEROXIDE TYPE C, SOLID3105ORGANIC PEROXIDE TYPE D, LIQUID3106ORGANIC PEROXIDE TYPE D, SOLID3107ORGANIC PEROXIDE TYPE E, LIQUID3108ORGANIC PEROXIDE TYPE E, SOLID3109ORGANIC PEROXIDE TYPE F, LIQUID3110ORGANIC PEROXIDE TYPE F, SOLID
3105ORGANIC PEROXIDE TYPE D, LIQUID3106ORGANIC PEROXIDE TYPE D, SOLID3107ORGANIC PEROXIDE TYPE E, LIQUID3108ORGANIC PEROXIDE TYPE E, SOLID3109ORGANIC PEROXIDE TYPE F, LIQUID3110ORGANIC PEROXIDE TYPE F, SOLID
3106ORGANIC PEROXIDE TYPE D, SOLID3107ORGANIC PEROXIDE TYPE E, LIQUID3108ORGANIC PEROXIDE TYPE E, SOLID3109ORGANIC PEROXIDE TYPE F, LIQUID3110ORGANIC PEROXIDE TYPE F, SOLID
3107ORGANIC PEROXIDE TYPE E, LIQUID3108ORGANIC PEROXIDE TYPE E, SOLID3109ORGANIC PEROXIDE TYPE F, LIQUID3110ORGANIC PEROXIDE TYPE F, SOLID
3108ORGANIC PEROXIDE TYPE E, SOLID3109ORGANIC PEROXIDE TYPE F, LIQUID3110ORGANIC PEROXIDE TYPE F, SOLID
3109 ORGANIC PEROXIDE TYPE F, LIQUID 3110 ORGANIC PEROXIDE TYPE F, SOLID
3110 ORGANIC PEROXIDE TYPE F, SOLID
2. Require SDS to check technical name
3. Stowage On Deck and Clear of Living Quarter
a) keen as cool as practical
2 b) away from all sources of heat and ignition.
c) protect from radiant heat which includes direct sunlight.
4. Transhipment prohibited for 3101-3106.
3111 ORGANIC PEROXIDE TYPE B, LIQUID, TEMPERATURE CONTROLLED
3112 ORGANIC PEROXIDE TYPE B, SOLID, TEMPERATURE CONTROLLED
3112ORGANIC PEROXIDE TYPE B, SOLID, TEMPERATURE CONTROLLED3113ORGANIC PEROXIDE TYPE C, LIQUID, TEMPERATURE CONTROLLED
3112ORGANIC PEROXIDE TYPE B, SOLID, TEMPERATURE CONTROLLED3113ORGANIC PEROXIDE TYPE C, LIQUID, TEMPERATURE CONTROLLED3114ORGANIC PEROXIDE TYPE C, SOLID, TEMPERATURE CONTROLLED
3112ORGANIC PEROXIDE TYPE B, SOLID, TEMPERATURE CONTROLLED3113ORGANIC PEROXIDE TYPE C, LIQUID, TEMPERATURE CONTROLLED3114ORGANIC PEROXIDE TYPE C, SOLID, TEMPERATURE CONTROLLED3115ORGANIC PEROXIDE TYPE D, LIQUID, TEMPERATURE CONTROLLED
3112ORGANIC PEROXIDE TYPE B, SOLID, TEMPERATURE CONTROLLED3113ORGANIC PEROXIDE TYPE C, LIQUID, TEMPERATURE CONTROLLED3114ORGANIC PEROXIDE TYPE C, SOLID, TEMPERATURE CONTROLLED3115ORGANIC PEROXIDE TYPE D, LIQUID, TEMPERATURE CONTROLLED3116ORGANIC PEROXIDE TYPE D, SOLID, TEMPERATURE CONTROLLED
3112ORGANIC PEROXIDE TYPE B, SOLID, TEMPERATURE CONTROLLED3113ORGANIC PEROXIDE TYPE C, LIQUID, TEMPERATURE CONTROLLED3114ORGANIC PEROXIDE TYPE C, SOLID, TEMPERATURE CONTROLLED3115ORGANIC PEROXIDE TYPE D, LIQUID, TEMPERATURE CONTROLLED3116ORGANIC PEROXIDE TYPE D, SOLID, TEMPERATURE CONTROLLED3117ORGANIC PEROXIDE TYPE E, LIQUID, TEMPERATURE CONTROLLED
3112ORGANIC PEROXIDE TYPE B, SOLID, TEMPERATURE CONTROLLED3113ORGANIC PEROXIDE TYPE C, LIQUID, TEMPERATURE CONTROLLED3114ORGANIC PEROXIDE TYPE C, SOLID, TEMPERATURE CONTROLLED3115ORGANIC PEROXIDE TYPE D, SOLID, TEMPERATURE CONTROLLED3116ORGANIC PEROXIDE TYPE D, SOLID, TEMPERATURE CONTROLLED3117ORGANIC PEROXIDE TYPE D, SOLID, TEMPERATURE CONTROLLED3118ORGANIC PEROXIDE TYPE E, SOLID, TEMPERATURE CONTROLLED
3112ORGANIC PEROXIDE TYPE B, SOLID, TEMPERATURE CONTROLLED3113ORGANIC PEROXIDE TYPE C, LIQUID, TEMPERATURE CONTROLLED3114ORGANIC PEROXIDE TYPE C, SOLID, TEMPERATURE CONTROLLED3115ORGANIC PEROXIDE TYPE D, LIQUID, TEMPERATURE CONTROLLED3116ORGANIC PEROXIDE TYPE D, SOLID, TEMPERATURE CONTROLLED3117ORGANIC PEROXIDE TYPE E, LIQUID, TEMPERATURE CONTROLLED3118ORGANIC PEROXIDE TYPE E, SOLID, TEMPERATURE CONTROLLED3119ORGANIC PEROXIDE TYPE F, LIQUID, TEMPERATURE CONTROLLED
3112ORGANIC PEROXIDE TYPE B, SOLID, TEMPERATURE CONTROLLED3113ORGANIC PEROXIDE TYPE C, LIQUID, TEMPERATURE CONTROLLED3114ORGANIC PEROXIDE TYPE C, SOLID, TEMPERATURE CONTROLLED3115ORGANIC PEROXIDE TYPE D, SOLID, TEMPERATURE CONTROLLED3116ORGANIC PEROXIDE TYPE D, SOLID, TEMPERATURE CONTROLLED3117ORGANIC PEROXIDE TYPE D, SOLID, TEMPERATURE CONTROLLED3118ORGANIC PEROXIDE TYPE E, SOLID, TEMPERATURE CONTROLLED

X : Prohibited

IMO	UN No.	Proper Shipping Name	ON
	1649	MOTOR FUEL ANTI-KNOCK MIXTURE	R
	3483	MOTOR FUEL ANTI-KNOCK MIXTURE, FLAMMABLE	R
<i>(</i> 1		1. Packed in a new package, stuff max in 1 tier high only.	
6.1		2. On deck protect stow (Shaded from direct sunlight)	
	3507	URANIUM HEXAFLUORIDE, RADIOACTIVE MATERIAL, EXCEPTED PACKAGE, less than 0.1 kg per package,	
		non-fissile or fissile-excepted	X
6.2	ALL	Infectious Substances	X
7	ALL	Radioactive Materials	X
	2800	BATTERIES, WET, NON-SPILLABLE electric storage	R
	2794	BATTERIES, WET, FILLED WITH ACID electric storage	R
	2795	BATTERIES, WET, FILLED WITH ALKALI electric storage	R
8	3028	BATTERIES, DRY, CONTAINING POTASSIUM HYDROXIDE, SOLID electric storage	R
		USED Batteries shall be confirmed if they are Waste.	
		If it is waste, refer "WASTE".	
	2071	AMMONIUM NITRATE BASED FERTILIZER	R
		For loading on ONE charted vessels, Will require 5 working days to obtain owners approval.	
	2211	POLYMERIC BEADS, EXPANDABLE evolving flammable vapour	R
	3314		
		PLASTICS MOULDING COMPOUND in dough, sheet or extruded rope form, evolving flammable vapour	R
		1. Shall be carried in open-top container or live reefer or ventilated container. (Not accept One Door off container)	
		2. Stowage on deck and away from ignition source.	
		3. Container shall be marked with warning "CAUTION - MAY CONTAIN FLAMMABLE VAPOR". (as required by	
		SP965.4)	
		<in are="" case="" devices="" for="" live="" mechanical="" or="" reefer="" used="" ventilation=""></in>	
		Shipper should provide the following documents as SOC, and GDG shall consult GCAA for approval;	
		a) SDS	
		b) The certificate of explosion proof type of Reefer container or Ventilator.	
		c) Operating manual of Reefer or Ventilator.	
		d) Spare parts and emergency contact.	
		e) L/G (Ship's crew does not have any responsibility to damage of SOC Reefer units / Ventilation)	
9		<in case="" closed="" container=""></in>	
9		Shall provide L/G to protect requirement of SP965.2, and GDG shall consult GCAA for approval.	
		**Flexible bags are not acceptable in Closed CTU.	
	2216	FISHMEAL (FISHSCRAP), STABILIZED Anti-oxidant treated. Moisture content greater than 5% but not exceeding	
		12%, by mass. Fat content not more than 15%	R
		1. Shall provide following documents to GDG	
		a) SDS	
		b) Fishmeal certificate.	
	2212	ASBESTOS, AMPHIBOLE (amosite, tremolite, actinolite, anthophyllite, crocidolite)	X
	2315	POLYCHLORINATED BIPHENYLS, LIQUID	Х
	2590	ASBESTOS, CHRYSOTILE	X
		POLYHALOGENATED BIPHENYLS, LIQUID or	
	3151	HALOGENATED MONOMETHYLDIPHENYLMETHANES, LIQUID or	X
		POLYHALOGENATED TERPHENYLS, LIQUID	
	2150	POLYHALOGENATED BIPHENYLS, SOLID or	
	3152	HALOGENATED MONOMETHYLDIPHENYLMETHANES, SOLID or POLYHALOGENATED TERPHENYLS, SOLID	Х
		FOLTRALOGENATED TERPHENTLS, SOLID	1

PROHIBITED & RESTRICTED CARGO LIST for ONE

(Dangerous Goods)

X : Prohibited

R : Restricted

IMO	UN No.	Proper Shipping Name	ONE
	3090	LITHIUM METAL BATTERIES (including lithium alloy batteries)	R
	3091	LITHIUM METAL BATTERIES CONTAINED IN EQUIPMENT (including lithium alloy batteries) or LITHIUM METAL BATTERIES PACKED WITH EQUIPMENT (including lithium alloy batteries)	R
	3480	LITHIUM METAL BATTERIES FACED with EQUIPMENT (including influin anoy batteries)	R
	3481	LITHIUM ION BATTERIES CONTAINED IN EQUIPMENT (including lithium-ion polymer batteries) or LITHIUM ION BATTERIES PACKED WITH EQUIPMENT (including lithium-ion polymer batteries)	R
		UN3090 / UN3480 - Prohibited from Origin ex-Yantain, Shekou, Dachan Bay, Nansha and Hong Kong USED and/or defective lithium batteries are prohibited. Only accept brand-new lithium batteries. Stowage : (LIBA) On Deck away from heat source is mandatory.	
		VEHICLE, FLAMMABLE GAS POWERED or VEHICLE, FLAMMABLE LIQUID POWERED or VEHICLE, FUEL CELL, FLAMMABLE GAS POWERED or	
	3166	VEHICLE, FUEL CELL, FLAMMABLE LIQUID POWERED	
		Hybrid Vehicle powered by Lithium Batteries shall be declared as DG. Stowage : (LIBA) On Deck away from heat source is mandatory (for HV - Hybrid Vehicle powered by Lithium Batteries)	R
		BATTERY-POWERED VEHICLE	
9	3171	Electric Vehicle only powered by Lithium Metal/Ion Battery shall be declared as DG. Electric Vehicle powered by both Lithium Metal/Ion Battery and other type of batteries shall be declared as DG. Stowage : (LIBA) On Deck away from heat source is mandatory (for EV - Electric Vehicle) powered by Lithium) Batteries	R
		USED and/or defective EV powered by Lithium Battery is prohibited.	X
	3536	LITHIUM BATTERIES INSTALLED IN CARGO TRANSPORT UNIT lithium-ion batteries or lithium metal batteries USED and/or defective lithium batteries are prohibited. Only accept brand-new lithium batteries. Stowage : (LIBA) On Deck away from heat source is mandatory.	R
	3359	FUMIGATED CARGO TRANSPORT UNIT	R
		 On deck stow only If under desk stowage is required, "Gas Detector" shall be provided by COL. 	
	3496	BATTERIES, NICKEL METAL HYDRIDE	R
		USED Batteries shall be confirmed if they are Waste. If it is waste, refer "WASTE".	
	3077	ENVIRONMENTALLY HAZARDOUS SUBSTANCE, SOLID, N.O.S. <restrictions (sodium<br="" applicable="" calcium="" chemical="" hypochlorite,="" is="" name="" only="" sdid="" technical="" the="" to,="" when="">Dichloroisocyanurate Dihydrate)> Commodity with technical name as Calcium Hypochlorite or SDID – origin from China is prohibited. Stowage On Deck away from sunlight In cases whereby commodity with technical name as Calcium Hypochlorite, acceptance is subjected to ONE dg policy Calcium Hypochlorite restriction.</restrictions>	R

<<Remark & Abbreviation>> GDG - Global DG Desk GCAA - Global Cargo Assessment & Acceptance C/P - Charter Party L/G - Letter of Guarantee CSC - Convention for Safe Containers

SDS - Safety Data Sheet

MnR - Maintain and Repair

SOC - Shipper Owned Container CTU - Closed Transport Unit

New / Brand new - direct from manufacturing plant